

ISD-325 coating

Features	Sound damping and thermal insulating coating with the following features: good adhesion, excellent flexibility, high mechanical and chemical resistance.
Colour (dry film)	Grey
Coverage rate	1.8 ÷ 4.5 kg/m ² referred to thickness of 1.0 ÷ 2.5 mm (dry film)
Specific gravity	1.07 kg/l (± 0.02)
Viscosity	35000 ÷ 50000 mPa·s Brookfield RVT rpm 20 s 7
Recommended thickness	First coat up to 3 mm wet film (about 1.7 mm dried). A second coat can be applied with thickness up to 4 ÷ 5 mm wet film (if needed).
Storage life	12 months in original sealed container.
Supports	Steel, galvanised plate, aluminium, wood, glass, fibreglass or plastic materials.

For further information, please refer to the technical data sheet.



ISD-325 has got an International Certification "ARAI" according to the ISO 10140-2/ASTM E-90 Normative and related to its sound damping properties on metal surfaces.

